

FORM PTO-1390 (Modified)
(REV 10-95)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

1382

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/720844

INTERNATIONAL APPLICATION NO.
PCT/EP 99/07545INTERNATIONAL FILING DATE
OCTOBER 8, 1999PRIORITY DATE CLAIMED
OCTOBER 15, 1998

TITLE OF INVENTION

SHAPING TOOL WITH A STRUCTURED SURFACE FOR PRODUCING STRUCTURES ON GLASS, AND THE
APPLICATION THEREOF FOR STRUCTURING CHANNEL PLATES

APPLICANT(S) FOR DO/EO/US

Rudolf SINGER, Joachim DISAM, Christiane BAUM

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☐ A copy of the International Search Report (PCT/ISA/210).
8. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
9. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
10. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
11. ☐ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 13 to 18 below concern document(s) or information included:

13. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
A **SECOND** or **SUBSEQUENT** preliminary amendment.
16. ☐ A substitute specification.
17. ☐ A change of power of attorney and/or address letter.
18. ☒ Certificate of Mailing by Express Mail
19. ☐ Other items or information:

EF 215 952581 US

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.53) 09/720844		INTERNATIONAL APPLICATION NO. PCT/EP 99/07545		ATTORNEY'S DOCKET NUMBER 1382	
--	--	--	--	----------------------------------	--

20. The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :				CALCULATIONS PTO USE ONLY	
<input type="checkbox"/> Search Report has been prepared by the EPO or JPO \$930.00					
<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) \$720.00					
<input type="checkbox"/> No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)) \$790.00					
<input checked="" type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$1,070.00					
<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4) \$98.00					
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$1,000.00	
Surcharge of \$130.00 for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.492 (e)). <input type="checkbox"/> 20 <input type="checkbox"/> 30				\$0.00	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	18 - 20 =	0	x \$18.00	\$0.00	
Independent claims	1 - 3 =	0	x \$80.00	\$0.00	
Multiple Dependent Claims (check if applicable). <input type="checkbox"/>				\$0.00	
TOTAL OF ABOVE CALCULATIONS =				\$1,000.00	
Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) (check if applicable). <input type="checkbox"/>				\$0.00	
SUBTOTAL =				\$1,000.00	
Processing fee of \$130.00 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492 (f)). <input type="checkbox"/> 20 <input type="checkbox"/> 30				\$0.00	
TOTAL NATIONAL FEE =				\$1,000.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). <input checked="" type="checkbox"/>				\$40.00	
TOTAL FEES ENCLOSED =				\$1,040.00	
				Amount to be:	
				refunded	\$
				charged	\$

☐ A check in the amount of _____ to cover the above fees is enclosed.


☒ Please charge my Deposit Account No. **19-4675** in the amount of **\$1,040.00** to cover the above fees.
 A duplicate copy of this sheet is enclosed.

☒ The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. **19-4675** A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

STRIKER, STRIKER & STENBY
103 EAST NECK ROAD
HUNTINGTON, NEW YORK 11743


 SIGNATURE

MICHAEL J. STRIKER
 NAME

27233
 REGISTRATION NUMBER

DECEMBER 29, 2000
 DATE

09/720844

526 Rec'd PCT/PTO 29 DEC 2000

UNITED STATES PATENT AND TRADEMARK OFFICE

Examiner: Group: Attorney Docket # 1382

Applicant(s) : SINGER, R., ET AL

Serial No. :

Filed : Simultaneously

For : SHAPING TOOL WITH A STRUCTURED SURFACE
FOR PRODUCING STRUCTURES ON GLASS...

SIMULTANEOUS AMENDMENT

December 29, 2000

Honorable Commissioner of Patents and Trademarks
Washington, D.C. 20231

S I R S:

Simultaneously with filing of the above identified application
please amend the same as follows:

In the Claims:

Claim 3 line 1 delete "or 2".

Claim 5 line 1 delete "or 4".

Claim 6 line 1 delete "one of claims 1 through 5", substitute with "claim 1".

Claim 7 line 1 delete "one of claims 1 through 6", substitute with "claim 1".

Claim 8 line 1 delete "one of claims 1 though 7", substitute with "claim 1".

Claim 9 line 1 delete "one of claims 1 though 8", substitute with "claim 1".

Claim 10 line 1 delete "one of claims 1 though 9", substitute with "claim 1".

Claim 11 line 1 delete "one of claims 1 though 10", substitute with "claim 1".

Claim 12 line 1 delete "or 11".

Claim 13 line 1 delete "one of claims 1 through 12", substitute with "claim 1".

Claim 15 line 1 delete "one of claims 1 through 14", substitute with "claim 1".

Claim 16 line 1 and 2 delete "or one of the following claims".

Claim 17 line 1 and 2 delete "or one of the following claims".

Claim 18 line 1 and 2 delete "one of claims 1 through 17", substitute with "claim 1".


REMARKS:

This Amendment is submitted simultaneously with filing of the above identified application.

With the present Amendment applicant has amended the claims so as to eliminate their multiple dependency.

Consideration and allowance of the present application is most respectfully requested.

Respectfully submitted,




Michael J. Striker
Attorney for Applicant(s)
Reg. No. 27233

(51) Internationale Patentklassifikation ⁷ : C03B 13/08, 13/14, 13/16, 23/02	A1	(11) Internationale Veröffentlichungsnummer: WO 00/21894 (43) Internationales Veröffentlichungsdatum: 20. April 2000 (20.04.00)
(21) Internationales Aktenzeichen: PCT/EP99/07545 (22) Internationales Anmeldedatum: 8. Oktober 1999 (08.10.99) (30) Prioritätsdaten: 198 47 549.7 15. Oktober 1998 (15.10.98) DE (71) Anmelder (für alle Bestimmungsstaaten ausser GB JP KR SG US): SCHOTT GLAS [DE/DE]; Hattenbergstrasse 10, D-55122 Mainz (DE). (71) Anmelder (nur für GB KR SG): CARL-ZEISS-STIFTUNG trading as SCHOTT GLAS [DE/DE]; Hattenbergstrasse 10, D-55122 Mainz (DE). (71) Anmelder (nur für JP): CARL-ZEISS-STIFTUNG [DE/DE]; D-89518 Heidenheim an der Brenz (DE). (72) Erfinder; und (75) Erfinder/Anmelder (nur für US): SINGER, Rudolf [DE/DE]; Am Sportfeld 1, D-55270 Engelstadt (DE). DISAM, Joachim [DE/DE]; Am Römertor 12, D-55116 Mainz (DE). BAUM, Christiane [DE/DE]; St.-Jakob-Strasse 33, D-07743 Jena (DE).		(74) Anwälte: FUCHS, Jürgen, H. usw.; Abraham-Lincoln-Strasse 7, D-65189 Wiesbaden (DE). (81) Bestimmungsstaaten: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO Patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), eurasisches Patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), europäisches Patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI Patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Veröffentlicht <i>Mit internationalem Recherchenbericht.</i>

(54) Title: SHAPING TOOL WITH A STRUCTURED SURFACE FOR PRODUCING STRUCTURES ON GLASS, AND THE APPLICATION THEREOF FOR STRUCTURING CHANNEL PLATES

(54) Bezeichnung: FORMGEBUNGSWERKZEUG MIT STRUKTURIERTER OBERFLÄCHE ZUM ERZEUGEN VON STRUKTUREN AUF GLAS UND SEINE ANWENDUNG BEI DER STRUKTURIERUNG VON KANALPLATTEN



(57) Abstract

Glasses with a determined, precise surface structuring are required in the area of glasses which have optic functions, for example, in display panels of new generation flat display screens, so-called channel plates. While avoiding the disadvantages of prior art screen printing technology, the invention provides a shaping tool (1) which has a structured surface for producing structures on glass (2) and which makes it possible to economically form highly precise microstructures by locally heating the glass region to be structured. The inventive shaping tool comprises a rolling cylinder (3) with a metallic hollow cylinder (7), a shaping sheet metal (8) fixed on the surface of said hollow cylinder, and a traversing shaft (5) for continuously driving the rolling cylinder (3) via drive elements (4). An electric heater is arranged in an electrically insulated manner between the shaft (5) and the hollow cylinder (7).

(57) Zusammenfassung

Im Bereich von Gläsern mit optischen Funktionen werden Gläser mit einer bestimmten, präzisen Oberflächenstrukturierung gefordert, beispielsweise bei Displayscheiben der neuen Flachbildschirmgeneration, den sogenannten Kanalplatten. Unter Vermeidung der Nachteile der bisher ausgeübten Siebdrucktechnik sieht die Erfindung ein Formgebungswerkzeug (1) mit strukturierter Oberfläche zum Erzeugen von Strukturen auf Glas (2) vor, das auf wirtschaftliche Weise das Ausformen von hochpräzisen Mikrostrukturen durch eine lokale Erwärmung des zu strukturierenden Glasbereiches ermöglicht. Das erfindungsgemäße Formgebungswerkzeug weist einen Walzzylinder (3) mit einem metallischen Hohlzylinder (7) und einem daran flächig befestigten formgebenden Blech (8), sowie eine durchgehende Welle (5) zum kontinuierlichen Antrieb des Walzzylinders (3) über Mitnehmer (4) auf. Zwischen der Welle (5) und dem Hohlzylinder (7) ist elektrisch isoliert eine elektrische Heizung angeordnet.

3/PHTS

09/720844
526 Rec'd PCT/PTO 29 DEC 2000

SHAPING TOOL WITH STRUCTURED SURFACE FOR CREATING
STRUCTURES

ON GLASS, AND ITS USE IN STRUCTURING CHANNEL PLATES

Specification:

The invention relates to a shaping tool with a
structured surface for creating structures on glass in
the context of a hot-shaping method, which is employed
in particular for making precision structures in a
channel plate of flat screens.

Plate glass provided with precision structures is
needed for precision applications, in particular in the
field of glasses (that is, kinds of glass) that have
optical functions. Such glasses are for instance
display screens of new flat screen generations (PDPs or
plasma display panels, and PALCs or plasma addressed
liquid crystals). In the so-called channel plate of
these flat screen glasses, microscopic channel
structures for triggering individual rows or columns
are made, which extend over the entire active width or
height of the screen and in which plasma is ignited via
an electrical discharge. The boundary on both sides of
an individual channel is accomplished via rectangular
ribs, whose width is as slight as possible. To achieve
an adequate discharge volume, the height of the ribs is
substantially greater than their width. The spacing of
the ribs should be as slight as possible.

The channel plate thus represents the
microstructured glass backpanel of a PALC or PDP
display. It is shown in basic form and in detail on a

greatly enlarged scale in Fig. 7.

5 The channel-like microstructuring shown in this
drawing figure must be accomplished cost-effectively
and in large numbers for different display sizes
(diagonal screen sizes up to 55 inches). For a 42-inch
HiVision PDP display, for instance, approximately 5760
channels with a pitch "X" of approximately $161\text{ m}\mu$ and a
rib height Y of $150\text{ m}\mu$ and a rib width "Z" of 30 to 50
10 $\text{m}\mu$, with tolerances of only a few micrometers over a
length of about 520 mm must be made. These enormously
stringent specifications dictate a high- precision
method and a corresponding apparatus.

5 It is known to create structures on glass on the
basis of a shaping tool with a structured surface,
using hot- shaping techniques.

20 Conventional hot-shaping methods, so-called
creative forming methods, are conceived such that hot
(molten) glass is given its desired form out of the
melt by means of a cooled shaping tool that is pressed
into the molten glass. The shaping tool takes on the
function of "solidification shaping"; that is, before
25 contact with the tool, the glass has a temperature
above the glass transition range (T_g) and is cooled by
the contact with the shaping tool in such a way that
the negative of the structured surface of the shaping
tool is copied dimensionally stably in the glass.

30 The invention takes as point of departure another
hot- shaping method, which can be characterized as a
reshaping warm-shaping process. In this reshaping
shaping process, the temperature of the glass before it
35 contacts the shaping tool having the structured surface

is optionally below the glass transition range, and is raised to the requisite temperature range for shaping ($T > T_g$) only by contact with the shaping tool. It is decisive here that only local heating of whatever region is to be structured occurs. In this reshaping process as well, the glass when it leaves the shaping tool is in its structured form and in a dimensionally stable state.

Physical variables, which pertain to both the conventional hot-shaping method and the reshaping warm-shaping method in terms of the process sequence are:

- the temperature of the glass and of the shaping tool;
- the pressure load on the glass and the shaping tool;
- the time of contact of the glass and shaping tool (dwell time).

The following description of the dwell time may make this clearer:

If the glass comes into contact with the shaping tool only briefly, or in other words if the shaping tool is removed from the glass before the solidification occurs, then because of the flowing of the glass structure, major rounding occurs in the structure after contact.

If contact is long-lasting, then major temperature differences and different thermal expansions of the shaping tool and glass result in intolerable lateral strains, which adversely affect the precision of the structures, or in other words the

precision with which the channels in channel plates can be positioned and reproduced.

5 A shaping tool which is intended to be
appropriate for precise process control must assure an
independent setting/regulation of the above-described
variables. The known hot-shaping tools do not meet
these requirements. Because of their conventional
solid structure with chromium nickel steels, which
10 necessitates heating the entire shaping tool
completely, they furthermore have inadequate thermal
dimensional stability, because at even relatively
slight temperature fluctuations in the shaping tool,
relatively major changes in length of the shaping
5 structures occurs, changes that exceed the allowable
tolerances for forming the channels or ribs.

20 The same applies to the shaping tool, disclosed
by German Patent DE 197 13 309 C1 and German Patent
Application DE 197 13 312 A1, with a structured surface
for creating structures on glass on the principle of
reshaping warm- shaping, which in the exemplary
embodiment has a rolling cylinder, comprising a solid
cylinder of preferably nonmetal material, to which a
25 molding tool with the structure-imparting surface is
clamped, resting relatively loosely. On each of the
two face ends of the solid cylinder, a respective
bearing journal for the rotational mounting of the
rolling cylinder is provided. An external heating
30 source is provided for the requisite local heating of
the shaping tool.

35 Such an embodiment of the shaping tool does not
make it possible in practice to create precision
structures with the desired replicable precision, since

the necessary thermal dimensional stability has not been adequately taken into account in the design of the individual components and in the bearing of the rolling cylinder. The enormously stringent specifications described at the outset can accordingly not be met.

With the shaping tool disclosed by European Patent Disclosure EP 0 866 487 A1 as well, the enormously stringent specifications discussed at the outset cannot be met.

This known shaping tool has a solid rolling cylinder comprising a metal alloy, and the shaping structures are formed directly on its circumferential surface. Nothing is said in the European Patent reference about the rotational support of the rolling cylinder. The glass substrate is plasticized by means of an external heat source before the rolling cylinder, which is not itself heated directly, in conjunction with a counterpart roller impresses the desired structure into the glass substrate.

This European reference again makes no statement as to the requirement for fine-tuning of the coefficients of thermal expansion and the bearing of the rolling cylinder in order to achieve the requisite thermal dimensional stability. In particular because of the solid rolling cylinder, even at slight temperature fluctuations, relatively major changes in length in the shaping structures occur, which exceed the allowable tolerances for forming the channels or ribs.

Producing channel plates by means of shaping tools with structured surfaces has therefore not gained

a foothold in the industry.

5 The production of channel plates is therefore currently done in general by screen printing, in which between 10 and 20 layers of glass solder are deposited, one layer at a time, onto the glass substrate.

This method has the following disadvantages:

10 · long process times
 · high solder costs
 · uneven sintering of the channel plates
 · environmental pollution (lead in the solder, etching solutions)

5 and therefore from a commercial standpoint allows the production only of prototypes; that is, it is not suited to commercial mass production.

20 It is the object of the invention to create a shaping tool with a structured surface for creating structures on glass that economically makes it possible to form high-precision microstructures in the glass by local heating of the region of glass to be structured, on the principle of reshaping warm-shaping.

25 This object is successfully attained by the invention by means of a shaping tool of this kind, having:

30 - a rolling cylinder, comprising a metal hollow cylinder, on whose outer jacket a metal shaping sheet, which is provided with recesses corresponding to the negative of the glass structures to be made, is put
35 into intimate large-area contact;

- a shaft, for continuously driving the rolling cylinder, that extends through the metal hollow cylinder;

5 - two drivers, which are fixedly mounted on the shaft at the level of the face ends of the metal hollow cylinder and are in positive operative engagement with the hollow cylinder; and

10 - an electric heater, which is disposed in electrically insulated fashion between the shaft and the metal hollow cylinder, with an additional thermal insulation from the shaft.

15 Because of the how the hot-shaping tool of the invention is constructed, it is economically possible, by simply rolling along the glass substrate, to form high- precision microstructures on the glass upon contact with the glass, by means of targeted local heating of the glass to be structured.

20 For attaining a constant reshaping temperature, the metal hollow cylinder plays a decisive role; by its thermal capacity, it prevents overly fast cooling upon contact with the glass. This effect is reinforced, in accordance with a feature of the invention, if the material comprising the metal hollow cylinder is a nickel wrought alloy.

25 In a further feature of the invention, the transmission of torque between the shaft and the rolling cylinder is established by providing that the drivers have at least three symmetrically distributed trapezoidal claws, and complementary trapezoidal
30 recesses, which are in mutual operative engagement with
35

the claws by small contact faces, are embodied on the face end of the metal hollow cylinder. This embodiment prevents an excessive outflow of heat from the rolling cylinder into the shaft. The construction is then free of play at temperature fluctuations within the component and at temperature differences from the rolling cylinder to the driver. As a result, the accuracy of concentricity is assured, or is always the same.

For production engineering reasons, expediently four claws offset by 90° are provided, but in principle any arbitrary number of claws greater than three is possible. The more claws there are, the more the connection corresponds to toothed gearing.

For the features of the invention, and in particular the disposition of the heater, are defined by the dependent claims.

Further characteristics and advantages of the invention will also become apparent from the description of exemplary embodiments of the invention shown in the drawings.

Shown are:

Fig. 1, in a longitudinal section, the construction of the hot-shaping roller according to the invention with a structure-bound rolling cylinder, driver, shaft and heater;

Fig. 1A, a sectional view through the roller of Fig. 1 taken along the line A-A;

Fig. 2, an enlarged detail of the roller of Fig. 1, in a plan view of the coupling of the shaft to the rolling cylinder via the drivers;

Fig. 3, a view of the heater, which is disposed between the shaft and the rolling cylinder of the shaping tool of Fig. 1 and serves to heat the rolling cylinder;

Fig. 4, an end-on front plan view on the shaping tool of Fig. 1, showing the slip ring contacts for supplying energy to the heater of Fig. 3;

Fig. 5, a greatly enlarged detail of the structure- imparting PtAu5 plate which surrounds the roller, for a PDP structure;

Fig. 6, a view corresponding to Fig. 5, but for a PALC structure instead;

Fig. 7, a detail showing a structured channel plate of known channel structure.

In Fig. 1, in a longitudinal section, the basic construction of a preferred embodiment of the hot-shaping tool of the invention is shown. The shaping tool has the shape of a roller generally identified by reference numeral 1, which is rolled continuously at a high contact pressure over a glass substrate 2 (Fig. 1A) to be structured, in that the glass substrate 2 is pulled through in the direction of the arrow under the shaping roller 1.

Special demands must be made of the glass substrate.

The production of channel plates for display systems, to which the invention preferably pertains, generally requires high-quality, specially-developed glass substrates 2, which are distinguished by robust process performance in all the production steps involved. Along with the extreme smoothness of the glass substrates, which is responsible in the final analysis for contrast sharpness and image resolution quality, temperature resistance, chemical resistance, low weight, and an adapted thermal expansion behavior are required.

The demands made of the ideal glass substrate for modern display technologies can be expressed in general and in terms of trends as being flatter, thinner and smoother, and at the same time having the most inert possible and sturdiest possible behavior in the complicated method steps, which are of quite different types depending on the type of display, and also being available at a favorable price (in large dimensions).

Boron silicate glasses play an outstanding role in many technically oriented glass applications. Because there is an inexhaustible number of possible chemical composition variations, extraordinary properties are attainable for this glass family. These glasses are especially distinguished by high temperature resistance, low thermal expansion, and good chemical resistance to aggressive media. Furthermore, such glasses can be produced even without adding alkaline components. These special properties afford access to new and technologically quite promising modern plate-glass applications.

From the above-described operative principle of

flat screens, the following guideline demands of a glass substrate for a channel plate can be derived:

- high temperature resistance ($T_g \geq 600^\circ\text{C}$)
- low density ($< 2.8 \text{ g/cm}^3$)
- excellent surface quality (planarity, warp, waviness, etc.)
- low shrinkage ($\leq 20 \text{ ppm}$)
- no "thermal sag"
- optimal adaptation of the thermal expansion
- high electrical resistance
- low gas permeability
- high transmission
- adequate mechanical strength
- large dimensions
- cost-effective

Along with the Corning overflow fusion method and the down-draw technology, float technology above all allows the cost-effective manufacture of large-size glass substrates with excellent surface qualities and with properties adapted to the production process for the display in question.

The embodiment of the shaping tool 1 is determined by the specific demands listed at the outset.

These involve essentially furnishing the following:

- a structured shaping tool for creating the glass structure;
- a shaping tool resistant to bending, for absorbing the rolling forces;

- a shaping tool for continuous production (which is attained by means of the roller structure); and
- a regulatable hot tool.

5

These conditions are met by the shaping roller 1 shown, which is constructed of four central components. These four central components are: a rolling cylinder 2, two drivers 4, a shaft 5, and a heater 6, which for the sake of clarity is shown separately in Fig. 3.

10

The rolling cylinder 3 forms the shaping part of the tool, because it carries on it the negative of the structure to be created. The rolling cylinder first comprises a load-bearing metal hollow cylinder 7, for instance with a length of 300 mm, an outer diameter of 120 mm, and a wall thickness of 12 mm.

15

The material comprising the rolling cylinder is preferably a nickel wrought alloy with the material No. 2.4816. The advantage of a metal alloy over a ceramic material is the high coefficient of thermal expansion of metals, which compared with ceramics is only slightly different from glass coefficients. The following table shows examples of differential expansion coefficients of various materials that can be used:

20

25

Material Category	Material	Differential Coefficient of Expansion at 800°C	Difference in Differential Coefficient of Expansion from the Glass Coefficient
5			
Glass	AF45	$\alpha_{800^{\circ}\text{C}} \approx 37 \cdot 10^{-6}/\text{K}$	
10 Ceramic	Quarzal	$\alpha_{800^{\circ}\text{C}} \approx 0.5 \cdot 10^{-6}/\text{K}$	$\Delta\alpha_{800^{\circ}\text{C}} \approx 36.5 \cdot 10^{-6}/\text{K}$
Metal	Inconel	$\alpha_{800^{\circ}\text{C}} \approx 20 \cdot 10^{-6}/\text{K}$	$\Delta\alpha_{800^{\circ}\text{C}} \approx 17 \cdot 10^{-6}/\text{K}$

15 If temperature fluctuations occur during the rolling, the dimensional deviation of the product is less, because of the small difference in the coefficients of expansion of the metal roller and glass, than if a ceramic roller is used.

20 The calculation below is intended to illustrate the subject matter more clearly.

25 The tolerance in a structure in the glass, over a substrate length of 100 mm, should amount for instance to no more than $\pm 10 \mu\text{m}$. Within the allowable amount of temperature fluctuations, the advantage of a metal roller over a ceramic roller is quite apparent. For the metal tool, a temperature difference of ± 4.8 kelvins (K) is still possible, while a ceramic tool allows a temperature fluctuation of only $\pm 2.8\text{K}$. Dimensional deviations resulting from an uneven temperature distribution in the tool can be eliminated by means of a corrective tool contour design (such as a convex or concave form of the jacket face).

35 A metal sheet 8 with a thickness of 1 mm, for example, into which the negative of the glass structure required has

been machine, is applied over the entire circumference to the outer surface of the metal hollow cylinder 7. For reasons of scale, these negative contours cannot be shown in Fig. 1. They can be inferred from the greatly enlarged detail views in Figs. 5 and 6, specifically for a PDP channel structure in Fig. 5 and for a PALC structure in Fig. 6. The recesses in the sheet 8 are therefore complementary to the ribs in the channel plate of Fig. 7.

One important aspect in terms of process suitability and economy is the material used for the sheet 8.

Tools that are used in the field of hot shaping of glass in fact make extremely stringent demands of the tool material to be employed. In selecting the material, the following criteria must therefore be taken into account:

- no tendency to adhere to the glass
- no corrosion or oxidization
- high thermal strength (durability)
- low wear
- cost-effectiveness.

For the rolling tool of Fig. 1, which is intended to use in microstructuring glass, the following additional demands must be met:

- microstructurability
- heatability (good thermal conduction)

Scientific material testing and long years of experience in the manufacture of shaping tools for hollow glass shaping have shown that platinum or platinum alloys, such as PtAu5 alloys, with a pure PtAu5 material or alternatively with an oxide-dispersed PtAu5 material (ODS),

best meet the demands made in terms of little tendency to adhere to glass and little corrosion or oxidization.

However, these materials have low thermal resistance, are not optimally wear-resistant, and are moreover very expensive. The low thermal resistance, which causes a loss of structure accuracy in the rolling tool, is disadvantageously expressed accordingly in the glass structure as well.

The material wear resulting from the low hardness of the PtAu5 material does on the other hand offer the important advantage of allowing mechanical, metal-cutting machining of the structuring. The requirement for high abrasion resistance makes for corresponding difficulties in microstructuring, yet is the essential prerequisite to the use of the roller. It is up to one skilled in the art to find the optimal compromise for a specific application.

Instead of the PtAu5 alloy, it is also conceivable to use materials employed in the glass industry that are coated, in order to reduce their tendency to adhere or to increase their wear resistance, as the tool material.

The following material combinations are conceivable:

Bulk Materials:	Inconel	Coating materials:	SiC
	Nicrofer		BC/N
	Nimonic		TiC/N
	Udimet		TiAlN
	Incoloy		MoS ₂
	PM 2000		Pt, Au alloys
			Ni-P
			Hard gold

The goal in each case is a combination of materials that leads to a wear-resistant, microstructurable, heat-conducting material with an only slight (or no) tendency to adhere to the glass.

To improve the compatibility of the tool and glass and to improve the wear resistance of the surface, the metal sheet must be bonded very intimately with the fundamental metal hollow cylinder 7.

In a particular embodiment, the sheet 8 is hot-isostatically pressed on (hipped). This is a large-area diffusion welding process that involves a complete fusion of material.

Instead of the hot-isostatic pressing, in principle any method for surface refinement can be employed, and the corresponding metal, ceramic or refined coatings can be applied either before the structuring using the negative structure, or after.

The embodiment of the structures in the sheet 8 has a definitive influence on the quality of the glass structures to be made, because to make the microstructures in the glass, the glass must be made to flow into the rolling grooves 8a (Figs. 5 and 6). The nature of the microstructure (grooves extending all the way around the tool) has a major influence on the possibilities for mechanically anchoring the glass composition during the shaping. For this reason, extremely smooth channel flanks without undercuts are of enormous importance, if the hot-shaping process is to be successful. Another requirement is minimal roughness of the tool surface, since in the rolling operation the tool structure and any peaks and valleys or defects in it will be copied exactly in the deformed glass.

In summary, the following demands are made of the structured rolling tool:

- exact geometric copying of the negative of the glass structure required
- high smoothness and low roughness of the channel flanks and of the surface
- adherence to a requisite unmolding angle.

The microstructuring of the roller body 1 is dependent essentially on the machinability of the material comprising the metal sheet 8. In general, the following methods are conceivable:

- laser machining
- wire erosion
- grinding
- turning on a lathe
- embossing
- milling
- etching
- hobbing erosion

Each method makes different demands of the material to be structured.

In the industry, the following methods are especially worth considering:

- laser machining
- erosion
- grinding
- precision turning on a lathe;

precision turning by means of a monocrystalline natural

diamond is especially important for microstructuring, as tests have shown.

For turning the hollow rolling cylinder 3, the
5 aforementioned drivers 4, which are fixedly disposed on the
shaft 5, are provided.

The drivers 4 therefore serve to transmit torque
between the shaft 5 and the rolling cylinder 3. The
10 connection of the drivers with the rolling cylinder is formed
by four trapezoidal claws 4a (Fig. 2) each that are in
operative engagement, with play, with four trapezoidal
grooves 3a formed, extending radially, on both ends of the
rolling cylinder 3. This number is solely an example. There
5 may also be three, six or eight pairs of claws in symmetrical
distribution, or any other number greater than three.

This claw drive with clearance on the one hand, by its
geometrical shape, enables axial and radial thermal
20 expansions, or in other words different thermal expansions
between the cylinder and the driver, and on the other,
because only small surface areas contact another, allows only
slight heat losses from the rolling cylinder to the drivers.

This drive construction makes it possible, to great
25 advantage for the accuracy of the microstructures, to achieve
a defined position of the rolling cylinder despite the
considerable thermal expansions.

To minimize coupling (the input of inductive power)
30 with the attendant power loss, the drivers 4 are provided
with axial slits 4b (Fig. 2) on the side toward the rolling
cylinder.

35 The metal material used for the drivers 4 is

preferably the same as for the rolling cylinder (material No. 2.4816), which has sufficient strength at the high operating temperatures.

5 The shaft 5 connects a drive mechanism 9, indicated symbolically on the face end, with the drivers 4 and carries both the heater 6 and its hookups 6a, 6b. It is supported in locating-nonlocating bearings 12, 13 with prestressed
10 precision spindle bearings, which allow freedom of axial and radial play. The torque between the shaft 5 and the drivers 4 is transmitted via a frictional engagement (bracing of the components). To protect against corrosion and wear, an Al_2O_3 coating is applied in the contact region of these components.

5 The drivers and the shaft 5 are axially braced against one another by means of shaft nuts 10 and cup springs 11 and therefore, because of their disposition, allow different thermal expansions between the drivers/rolling cylinder and the shaft. The shaft 5 in this arrangement takes on the
20 function of a tie rod, which leads to increased rigidity of the rolling cylinder 3.

25 To make it possible to dispose the current supply leads - to be described hereinafter - for the heater, the conduits for the air cooling and the hookups for the thermocouple (temperature measurement), the shaft 5 is embodied as a hollow shaft. To keep the power losses in the shaft during electric heating slight, the shaft is made with six longitudinal slits 5a (Fig. 1A) distributed uniformly
30 over the circumference; this prevents induction current losses from developing in the shaft.

 The shaft 5 preferably comprises the highly heat-resistant material No. 2.4879.

The heater 6 is disposed in the region between the rolling cylinder 3 and the shaft 5. Acting as the hot conductor is a PtRh10 strip 6c (20 by 1.5 mm), which is wound in grooves 14a of a ceramic cylinder 14 into a coil as shown in Fig. 3.

This ceramic cylinder 14 insulates the shaft 5 both electrically and thermally from the hot conductor 6c. Quarzal can be used in particular as the material for the ceramic cylinder.

The rolling cylinder 3 is electrically insulated from the hot conductor 6c by an approximately 2 mm thick quartz glass tube 15. The slight spacing assures fast, low-loss heat transmission, and the transmission properties of the quartz glass assure a good exchange of radiation.

Because of the aforementioned geometric construction, both indirect heating (resistance heating) and direct heating (inductive heating) of the rolling cylinder are possible. The heat required for the manufacturing process can be varied in a known manner by regulating the voltage potential or the current intensity.

Instead of the hot conductor strip 6c, other geometries may be employed, in particular wire, rod or tube profiles. Still other hot conductor materials, in particular kanthal or nicrothal alloys or noble metal alloys, can also be used as the material, depending on the thermal stress.

The supply of energy to the heater is accomplished by means of a slip ring contact assembly 16 on one shaft end, and rod elements 6a, 6b (Fig. 3) in the (hollow) shaft 5.

Fig. 4 in plan view shows further details of the slip

ring contact assembly 16. It fundamentally comprises four double-leg carbon holders 16a with silver graphite carbon 16b, which each slip in pairs on a respective cylinder portion 16c, to which a respective end of the current lead 6a, 6b (Fig. 3) is extended. Clamps 16d serve to hook up the supply lines.

To prevent overheating of the shaft 5, two ceramic tubes 17 are installed in the interior of the shaft, and by means of these tubes, cool air is blown into the center of the shaft; this air can exit again on both ends. A thermocouple 18 (Fig. 1A) in the middle of the coil, with a terminal 18a (Fig. 1) extended to the outside, makes it possible to monitor the temperature and regulate the heater.

This heater can be operated with air cooling as an ohmic resistance heater (50 Hz). As the type of heating, medium-frequency induction heating is optionally usable, which uses either copper (water-cooled) or noble metal (without cooling) as its electrical conductor.

The heater is an essential component of the shaping roller according to the invention, because the shaping process by reshaping, which is the point of departure for the invention, requires a targeted reheating of the glass substrate. This reheating is effected by purposefully heating the rolling cylinder 3 to a temperature that is higher than T_g , that is, the glass transition temperature of the glass to be structured. To create fine structures close to the shaping tool on only the surface of the substrate, accurate temperature control is necessary, in which the least toughness of the glass occurs in the boundary layer between the shaping tool and the glass. This requires a higher tool temperature in comparison to the glass temperature of the typically preheated glass substrate.

On the other hand, by means of the hot tool a temperature gradient is built up in the substrate, which leads to thermal stresses. The necessity of minimizing these stresses, in order to avoid breakage, determines the lower limit of the outset temperature of the glass before the shaping. In the depressurization range, it is above the T_g point (at a toughness of about $10 \text{ E} + 12 \text{ dPa s}$). In order then to influence the fundamental structure of the starting material as little as possible, the outset temperature of the glass should be kept as low as possible.

For the shaping, the temperature of the thin surface layer of the glass that is involved, by material transport, in the reshaping process is crucial. This shaping temperature is equivalent to a mixture of the temperatures of the tool and the glass before contact. Other essential influences are exerted by the properties of the components, such as thermal conductivity and thermal capacity. Since heat is flowing from the hot tool into the colder workpiece during the entire shaping time, a constant supply of heat to the tool at the contact point must be assured, so as to maintain the flow of material into the grooves. In the present case, this is done by means of heating the interior of the roller, which because of the solid metal hollow cylinder 7 has a high thermal capacity. A high tool temperature and hence a high boundary face temperature does speed up the shaping process, but also speeds up the heating throughout the specimen, which is of limited thickness and thereby loses so much stability that it is no longer possible to separate the intimately formed-on tool from the specimen without destroying the specimen. The destabilization if the temperature is raised and/or the shaping time is shortened can be ascribed to the severely bent toughness/temperature curve.

The requisite shaping time for forming a desired structure, particularly ribs whose height is greater than their width, is determined by flow events into a gap. The limiting factors are as follows:

- pressure: linear
- toughness: linear
- height: quadratic
- width: quadratic

Suitable deformation times in the rolling process, for a roller 120 mm in diameter (shaping engagement width approximately 3 mm) are on the order of 1.5 seconds (rolling speed: 2 mm/sec).

The shaping forces are generated by pressing the shaping roller 1 against the softening (viscous) glass. They thus occur in the form of internal pressure in a liquid, and not as stresses, as long as the shaping speeds remain low enough. The pressure that triggers the flowing of the glass into the gaps 8a of the tool is thus determined as force/contact area of the roller on the glass 2. This area is dependent on the roller diameter and on the depth to which the roller is lowered, and thus also on the shaping temperature.

The shaping roller according to the invention, by its construction, enables a suitable kind of process control, which in a way that was previously impossible leads to precise microstructuring by precise adherence to the aforementioned reshaping parameters.

Claims

1. A shaping tool (1) with a structured surface for creating structures on glass (2), having

- a rolling cylinder (3), comprising a metal hollow cylinder (7), on whose outer jacket a metal shaping sheet (8), which is provided with recesses (8a) corresponding to the negative of the glass structures to be made, is put into intimate large-area contact;

- a shaft (5) for continuously driving the rolling cylinder (3), which shaft extends through the metal hollow cylinder (7);

- two drivers (4), which are fixedly mounted on the shaft (5) at the level of the face ends of the metal hollow cylinder (7) and are in positive operative engagement with the hollow cylinder (7); and

- an electric heater (6), which is disposed in electrically insulated fashion between the shaft (5) and the metal hollow cylinder (6), with an additional thermal insulation from the shaft.

2. The shaping tool of claim 1, characterized in that the material comprising the metal hollow cylinder (7) is a nickel wrought alloy, preferably such an alloy identified by material No. 2.4816.

3. The shaping tool of claim 1 or 2, characterized in that the material of the shaping sheet (8) comprises a wear-resistant, microstructurable, heat-conducting material with the least possible inclination to adhere to the glass.

4. The shaping tool of claim 3, characterized in that the sheet (8) comprises a PtAu5 alloy, with a pure PtAu5 material or alternatively with an oxide-dispersed PtAu5 material.

5. The shaping tool of claim 3 or 4, characterized in that the sheet (8) comprises a foundation material with a coating applied to it.

6. The shaping tool of one of claims 1 through 5, characterized in that the shaping sheet (8) is hot-isostatically pressed (hipped) onto the metal hollow cylinder (7).

7. The shaping tool of one of claims 1 through 6, characterized in that the structuring recesses (8a) are made in the shaping sheet (8) by precision turning using a diamond tool.

8. The shaping tool of one of claims 1 through 7, characterized in that the drivers (4) have at least three symmetrically distributed trapezoidal claws (4a), and complementary trapezoidal recesses (3a), which are in mutual operative engagement with the claws (4a) by small contact faces, are embodied on the face end of the metal hollow cylinder (7).

9. The shaping tool of one of claims 1 through 8, characterized in that the drivers (4) have axial slits (4b) toward the hollow cylinder.

10. The shaping tool of one of claims 1 through 9, characterized in that the shaft (5), embodied as a hollow shaft, is supported in locating-nonlocating bearings (12, 13) with prestressed spindle bearings.

11. The shaping tool of one of claims 1 through 10, characterized in that the drivers (4) and the shaft (5) are braced together axially in the manner of a tie rod by means of shaft nuts (10) and cup springs (11).

12. The shaping tool of claim 10 or 11, characterized in that the shaft (5) has a plurality of longitudinal slits (5a) distributed uniformly over its circumference.

13. The shaping tool of one of claims 1 through 12, characterized in that a ceramic cylinder (14) is slipped onto the shaft (5) in a manner secure against relative rotation and on its jacket receives the hot conductor (6c) of the electric heater (6), and that a quartz glass tube (15) for electrical insulation from the adjacent hollow roller (7) is slipped onto the ceramic cylinder (14) having the hot conductors (6c).

14. The shaping tool of claim 13, characterized in that a PtRh10 strip (6c) is provided as the hot conductor, and it wound into a coil in grooves (14a) of the ceramic cylinder 14.

15. The shaping tool of one of claims 1 through 14, characterized in that a slip ring assembly (16) is provided on the shaft (5), for supplying energy to the heater (6).

16. The shaping tool of claim 10 or one of the following claims, characterized in that at least one ceramic tube (17) for supplying cooling air is provided in the interior of the hollow shaft (5).

17. The shaping tool of claim 10 or one of the following claims, characterized in that a thermocouple (18) is installed in the interior of the hollow shaft (5).

18. The use of the shaping tool (1) of one of claims 1 through 17 for making precision structures in a channel plate of flat screens.

FIG. 1




FIG. 2




FIG. 1A




FIG. 3




FIG. 4




FIG. 5




FIG. 6





FIG. 7



Abstract

SHAPING TOOL WITH STRUCTURED SURFACE FOR CREATING STRUCTURES ON GLASS, AND ITS USE IN STRUCTURING CHANNEL PLATES

In the field of glasses with optical functions, glasses with a specific precise surface structuring are required, for instance in display screens of the new flat screen generation, or so-called channel plates.

While avoiding the disadvantages of the screen printing technique employed until now, the invention provides a shaping tool (1) with a structured surface for creating structures on glass (2) which in an economical way makes it possible to form high-precision microstructures by local heating of the region of glass to be structured. The fact that the invention has a rolling cylinder (3) with a metal hollow cylinder (7) and a shaping sheet (8) secured in surface contact to it, as well as a continuous shaft (5) for continuously driving the rolling cylinder (3) via drivers (4). Between the shaft (5) and the hollow cylinder (7), an electric heater is disposed in electrically insulated fashion.

(Fig. 1)

DECLARATION AND POWER OF ATTORNEY FOR NATIONAL STAGE OF PCT PATENT APPLICATION

As a below-named inventor, I hereby declare that:

Rudolf SINGER
Joachim DISAM
Christiane BAUM

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled **SHAPING TOOL WITH A STRUCTURED SURFACE FOR PRODUCING STRUCTURES ON GLASS, AND THE APPLICATION THEREOF FOR STRUCTURING CHANNEL PLATES** the specification of which was filed as PCT International Application number PCT/EP 99/07545 on October 8, 1999.

I hereby state that I believe the named inventor or inventors in this Declaration to be the original and first inventor or inventors of the subject matter which is claimed and for which a patent is sought.

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose all information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, Section 119(a)-(d) or Section 365 (b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate or PCT International application having a filing date before that of the application on which priority is claimed.

Prior foreign application(s):

Priority claimed:

<u>198 47 549.7</u>	<u>GERMANY</u>	<u>OCTOBER 15, 1998</u>	<u>X</u>	
(Number)	(Country)	(Date filed)	Yes	No
<u> </u>	<u> </u>	<u> </u>	<u> </u>	<u> </u>
(Number)	(Country)	(Date filed)	Yes	No

As a named inventor, I hereby appoint the following attorney to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

Michael J. Striker, Reg. No. 27233

Direct all telephone calls to Striker, Striker & Stenby at telephone no.: (631) 549 4700 and address and all correspondence to:

STRIKER, STRIKER & STENBY
103 East Neck Road
Huntington, New York 11743
U.S.A.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with

Year	1950	1951	1952	1953	1954	1955	1956	1957	1958	1959	1960	1961	1962	1963	1964	1965	1966	1967	1968	1969	1970	1971	1972	1973	1974	1975	1976	1977	1978	1979	1980	1981	1982	1983	1984	1985	1986	1987	1988	1989	1990	1991	1992	1993	1994	1995	1996	1997	1998	1999	2000	2001	2002	2003	2004	2005	2006	2007	2008	2009	2010	2011	2012	2013	2014	2015	2016	2017	2018	2019	2020	2021	2022	2023	2024	2025	2026	2027	2028	2029	2030	2031	2032	2033	2034	2035	2036	2037	2038	2039	2040	2041	2042	2043	2044	2045	2046	2047	2048	2049	2050	2051	2052	2053	2054	2055	2056	2057	2058	2059	2060	2061	2062	2063	2064	2065	2066	2067	2068	2069	2070	2071	2072	2073	2074	2075	2076	2077	2078	2079	2080	2081	2082	2083	2084	2085	2086	2087	2088	2089	2090	2091	2092	2093	2094	2095	2096	2097	2098	2099	2100																			
Population	1,000,000	1,050,000	1,100,000	1,150,000	1,200,000	1,250,000	1,300,000	1,350,000	1,400,000	1,450,000	1,500,000	1,550,000	1,600,000	1,650,000	1,700,000	1,750,000	1,800,000	1,850,000	1,900,000	1,950,000	2,000,000	2,050,000	2,100,000	2,150,000	2,200,000	2,250,000	2,300,000	2,350,000	2,400,000	2,450,000	2,500,000	2,550,000	2,600,000	2,650,000	2,700,000	2,750,000	2,800,000	2,850,000	2,900,000	2,950,000	3,000,000	3,050,000	3,100,000	3,150,000	3,200,000	3,250,000	3,300,000	3,350,000	3,400,000	3,450,000	3,500,000	3,550,000	3,600,000	3,650,000	3,700,000	3,750,000	3,800,000	3,850,000	3,900,000	3,950,000	4,000,000	4,050,000	4,100,000	4,150,000	4,200,000	4,250,000	4,300,000	4,350,000	4,400,000	4,450,000	4,500,000	4,550,000	4,600,000	4,650,000	4,700,000	4,750,000	4,800,000	4,850,000	4,900,000	4,950,000	5,000,000	5,050,000	5,100,000	5,150,000	5,200,000	5,250,000	5,300,000	5,350,000	5,400,000	5,450,000	5,500,000	5,550,000	5,600,000	5,650,000	5,700,000	5,750,000	5,800,000	5,850,000	5,900,000	5,950,000	6,000,000	6,050,000	6,100,000	6,150,000	6,200,000	6,250,000	6,300,000	6,350,000	6,400,000	6,450,000	6,500,000	6,550,000	6,600,000	6,650,000	6,700,000	6,750,000	6,800,000	6,850,000	6,900,000	6,950,000	7,000,000	7,050,000	7,100,000	7,150,000	7,200,000	7,250,000	7,300,000	7,350,000	7,400,000	7,450,000	7,500,000	7,550,000	7,600,000	7,650,000	7,700,000	7,750,000	7,800,000	7,850,000	7,900,000	7,950,000	8,000,000	8,050,000	8,100,000	8,150,000	8,200,000	8,250,000	8,300,000	8,350,000	8,400,000	8,450,000	8,500,000	8,550,000	8,600,000	8,650,000	8,700,000	8,750,000	8,800,000	8,850,000	8,900,000	8,950,000	9,000,000	9,050,000	9,100,000	9,150,000	9,200,000	9,250,000	9,300,000	9,350,000	9,400,000	9,450,000




Signature: 	Date: <u>Engelstadt</u> <u>11. 12. 2000</u>	Residence and Full Postal Address: Am Sportfeld 1 D-55270 <u>Engelstadt</u> <u>DEX</u> Germany
Full Name of First or Sole Inventor: <u>Rudolf SINGER</u>	Citizenship: GERMAN	
Signature: 	Date: <u>Mainz</u> <u>23. 11. 2000</u>	Residence and Full Postal Address: Am Roemertor 12 D-55116 <u>Mainz</u> <u>DEX</u> Germany
Full Name of Second Inventor: <u>Joachim DISAM</u>	Citizenship: GERMAN	
Signature: 	Date: <u>Jena</u> <u>5. 12. 00</u>	Residence and Full Postal Address: St.-Jacob-Strasse 33 D-07743 <u>Jena</u> <u>DEX</u> Germany
Full Name of Third Inventor: <u>Christiane BAUM</u>	Citizenship: GERMAN	
Signature:	Date:	Residence and Full Postal Address:
Full Name of Fourth Inventor:	Citizenship:	
Signature:	Date:	Residence and Full Postal Address:
Full Name of Fifth Inventor:	Citizenship:	
Signature:	Date:	Residence and Full Postal Address:
Full Name of Sixth Inventor:	Citizenship:	
Signature:	Date:	Residence and Full Postal Address:
Full Name of Seventh Inventor:	Citizenship:	
Signature:	Date:	Residence and Full Postal Address:
Full Name of Eighth Inventor:	Citizenship:	

FIG. 1




FIG. 2




FIG. 1A

